

Flooring

# Long Board



03/2019 B LD EN 10

**Schotten  
& Hansen**

Nature Refined.

# Long Board

## Product specifications

<b>Description</b>	Construction: Three-layer engineered board Top-Layer: Oak veneer, other types of wood on request Carrier: Softwood
<b>Length<sup>1</sup></b>	3000-5000 mm, in steps of 500 mm <sup>2</sup> ; proportionally short lengths up to 5 %.
<b>Width<sup>1</sup></b>	160-280 mm in fine selection 160-360 mm in medium selection 280-360 mm in coarse selection. In steps of 10 mm <sup>3</sup>
<b>Thickness<sup>1</sup></b>	Approx. 19 mm <sup>4</sup> (± 0.5 mm)
<b>Top-layer<sup>1</sup></b>	Approx. 4.5 mm; glued waterproof and formaldehyde-free.
<b>Surface</b>	Schotten & Hansen pre-finished, permeable surface. Surface treatment with natural oils, resins and waxes. Schotten & Hansen surfaces can be regenerated without sanding or mechanical treatment.
<b>Wood moisture content</b>	On delivery: approx. 8 % ex works. A special drying process during production reduces shrinkage and swelling behaviour of the floor boards after installation.
<b>Emissions</b>	Formaldehyde emission according to EN 14342: Class E1, measured as EN 717- 1 VOC-emission according ISO 16000: < 1 mg / m <sup>3</sup> .
<b>Fire behaviour classification</b>	Cfl – S 1 according to EN 14342:2013
<b>General building inspectorate approval</b>	Z-156.607-1528
<b>Further features</b>	Boards are grooved and tongued on the long sides, Face sides of the boards are grooved. Chamfer: approx. 0.7 mm, 30°. Other chamfer options on request.
<b>Installation</b>	Full bonding with permanently elastic adhesive. Installation according to DIN 18356. Requirement on subsoil: Installation-ready subsoil according to DIN 18356 and DIN 18202 chart 3, line 4 increased requirements. Recommended adhesive: BONA R850 or adhesive of equal quality (adhesive used for installation has to be approved by general building inspectorate); suitable for gluing the floorboards on screed.
<b>Underfloor heating</b>	Schotten & Hansen floorboards are well-suited for use in combination with underfloor heating with hot water or electrically. Heat conductivity $\lambda$ [W/(m*K)]: top layer oak 0.12 (calculated according to EN 14342:2013) Heat contact resistance R [m <sup>2</sup> K/W]: top layer oak 0.16 (calculated according to EN 14342:2013) Maximum surface temperature of the floorboards: 29° C.
<b>Cleaning &amp; Care</b>	Schotten & Hansen cleaning and caring products. Schotten & Hansen recommends the use of a floor polishing machine. For further information please see the cleaning and caring instructions or contact our service department: <a href="mailto:service@schotten-hansen.com">service@schotten-hansen.com</a>

<sup>1</sup> Dimensions may vary slightly due to production conditions. Distribution of lengths and widths according to production requirements.

<sup>2</sup> Possible fixed lengths: 1450, 1950, 2450, 3000, 3500, 4000, 4500, 5000 mm

<sup>3</sup> Possible fixed widths: 160, 170, 180, 190, 200, 210, 220, 230, 240, 250, 260, 270, 280, 290, 300, 310, 320, 330, 340, 350, 360 mm

<sup>4</sup> Other total thickness of boards possible on request.

# Long Board

## Colours<sup>5</sup>


01 Pearl	05 Antique Ivory	08 Sepia	12 Mocha	16 Black Cherry
02 Beach Shell	06.001 Oyster Dark	09 Corn Gold	13 Dark Clay	17 Linen
03 Honey Gold	06.002 Oyster Light	10 Cognac	14 Chocolate	18 Pebble Stone
04 Cinnamon	07 Smoke	11 Havana	15 Black Olive	19 Drift Wood

## Character Selection<sup>5</sup>

1 Fine (160-280 mm width)	Even and calm wood structure with few small knots and fine cracks, mended by hand.
2 Medium (160-360 mm width)	Distinct wood structure with knots, shrinkage and wind cracks, mended by hand.
3 Coarse (280-360 mm width)	Very lively wood structure with selected knots, distinctive shrinkage and wind cracks, mended by hand.

## Treatment<sup>5</sup>

1 Brushed	Accentuate the wood's typical grain structure by brushing out early wood.
2 Hand-planed	A landscape of small ridges and hollows award the boards a wavy structure for a vivid appearance.
3 Shrunken <sup>6</sup>	Special processes create an expressive surface with the character of naturally aged wood.



Colour between floorboards is subject to variations and display exhibits or samples, as far as these are due to the natural quality of the used material as well as customary.

<sup>5</sup> Available on request / selectable. Possibly not available in all colours and/or sizes. Customized products on request.

<sup>6</sup> Patented Schotten & Hansen surface treatment.

**Schotten  
& Hansen**

Schotten & Hansen GmbH, August-Moralt-Straße 1-3, 86971 Peiting, Germany  
T +49 8861 908 04-100, kontakt@schotten-hansen.com, www.schotten-hansen.com

# Long Board

## Further Information

### Indoor climate and wooden floor

Wood is a natural material that is adjusting to the indoor climate. Wood absorbs moisture from the air and releases it again.

We would like to point out that during the heating period, the floorboards might strongly dry out and thus develop shrinkage cracks. Cracks caused by low air humidity during the heating period do not justify complaint.

With the maintenance of a comfortable and healthy indoor climate of 20° C and 50% relative humidity during the heating season, you can largely avoid the negative effects of this natural phenomena.

Thermal- and hygrometers control the air in your rooms easily. In case the air is too dry, suitable measures for humidifying the air must be taken. We recommend you a humidifier control - hygrostat for obtaining a constant air humidity.

Installation should be carried out professionally by a trained Schotten & Hansen partner.

### Bonding

The preparation of the subsoil is to be carried out in accordance with the guidelines of the adhesive manufacturer and relevant DIN standards.

For the bonding of all Schotten & Hansen floor products we recommend a solvent-free and elastic adhesive.

In the process of glueing, full bonding to the subsoil and a sufficient contact pressure during the setting has to be ensured.

### Bonding on Screed

First, an inspection of the subsoil and the application requirements has to be conducted according to VOB Part B DIN 1961 and Part C DIN 18356.

Due to the large lengths and widths of some flooring products, increased care is required for the evenness of the subsoil.

### Installation on underfloor heating

All Schotten & Hansen long boards are to be fully bonded with elastic adhesive to underfloor heating. Prior to this, a thorough inspection of the heating screed's readiness for installation has to be carried out – in particular the heating protocol and the details of test points (pursuant to DIN standards) have to be documented by the screed layer. The adhesive must be suitable for bonding on an underfloor heating system.

Please observe the maximum surface temperature of 29° C.

Additionally, during a heating-period the air humidity should be improved. Otherwise the floorboards might strongly dry out and develop shrinkage cracks. Cracks caused by low air humidity during the heating period do not justify complaint.

### Important measurements prior to installation:

- Switch off underfloor heating three days before installation.
- Measure moisture content of the screed.
- Keep room climate constant at 45 % ± 5 % relative air humidity. This also applies for the next few days after the installation (during this time increase underfloor heating by 5° C per day).
- Prepare a heating protocol.

All information on this data sheet is to be considered as advice and is based on empirical investigations according to today's state of the art. Therefore, all provided information on the suitability, processing and application of our products, as well as technical advice and further particulars, do explicitly not release the customer and/or user from verifying the products' suitability by means of their own tests.

**Schotten  
&Hansen**